STANDARD FILTER PAPERS

APPLICATIONS

• The standard filter papers are made with 100% cellulose and can have various applications in hospitals/ medical, in research laboratories, in schools/universities, in industry such as chemical, pharmaceutical, cosmetic, water treatment, food...

filtraTECH's grades: ST60 | ST61 | ST62 | ST63 | ST64 | ST67.

✓ Available in sheets (F), plain discs (A) or folded discs (P).



| | | Smoo | th filter paper with me | dium filtration for gene | eral applications, econor | mical. | |
|--|------|----------------------------|-------------------------|--------------------------|-------------------------------------|----------------------------|---------------|
| | ST60 | Weight (g/m²) DIN 53104 | Thickness (mm) | Pore size (µm) | Filtration speed (sec) DIN 53137 | Burst strength (kg/cm²) | Vhatmar 93 |
| | | 64 | 0.15 | 10-20 | 50 | 1.45 | N // |

| | F | ilter paper for analytica | al works in laboratories | with medium filtration | | |
|------|----------------------------|---------------------------|--------------------------|-------------------------------------|----------------------------|--------------|
| ST61 | Weight (g/m²) DIN 53104 | Thickness (mm) | Pore size (µm) | Filtration speed (sec) DIN 53137 | Burst strength (kg/cm²) | Vhatmar 1 |
| | 73 | 0.16 | 5-13 | 88 | 1.95 | N/I |

| | | Smooth filter pap | per with fast filtration f | or general works. | | c |
|------|----------------------------|-------------------|----------------------------|-------------------------------------|----------------------------|----------------|
| ST62 | Weight (g/m²) DIN 53104 | Thickness (mm) | Pore size (µm) | Filtration speed (sec) DIN 53137 | Burst strength (kg/cm²) | Vhatman 114 |
| | 73 | 0.17 | 17-30 | 22 | 1.25 | N // |

| | | Thin fi | ilter paper with fast filt | ration. | | |
|------|----------------------------|----------------|----------------------------|-------------------------------------|----------------------------|--------------|
| ST63 | Weight (g/m²) DIN 53104 | Thickness (mm) | Pore size (µm) | Filtration speed (sec) DIN 53137 | Burst strength (kg/cm²) | Vhatman – |
| | 60 | 0.14 | 36-65 | 25 | 1.05 | N // |

| | | | Creped fil | ter paper with very fast | filtration. | | c |
|-----|-----|----------------------------|----------------|--------------------------|-------------------------------------|----------------------------|----------------|
| - H | 104 | Weight (g/m²) DIN 53104 | Thickness (mm) | Pore size (µm) | Filtration speed (sec) DIN 53137 | Burst strength (kg/cm²) | Whatman 113 |
| | | 120 | 0.35 | 40 | 11 | 0.75 | N // |

| | | | Very thin fi | lter paper with very fas | t filtration. | | |
|------|---|----------------------------|----------------|--------------------------|-------------------------------------|----------------------------|--------------|
| ст67 | > | Weight (g/m²) DIN 53104 | Thickness (mm) | Pore size (µm) | Filtration speed (sec) DIN 53137 | Burst strength (kg/cm²) | Whatmar – |
| | | 50 | 0.12 | 17-30 | 22 | 0.25 | N // |

7

Brewery industry filter paper

• This embossed filter paper 75 g/m² is ideally used for any sample preparation and for the clarification of malt analysis in breweries.

- ▶ filtraTECH's grade: FS97.
- ✓ Available in plain discs (A) or folded discs (P) in boxes of 100 units.

| O Diameter FS97A0150 Ø Diameter Code 185 mm FS97A0185 240 mm FS97P0240 240 mm FS97A0240 270 mm FS97P0270 | Ø Diameter | Code | P | ~ |
|--|------------|------|------------|------|
| 185 mm FS97A0185 240 mm FS97P0240 | | | Ø Diameter | Code |
| | | | - | |
| | | | | |

| Weight (g/m²) | Thickness (mm) | Filtration speed (sec) | // Whatman |
|---------------|----------------|------------------------|------------|
| 75 | 0.17 | 110 | 2555 |

Sugar industry filter paper

• Usable in the food industry, the filter papers for the sugar industry offer a fast filtration or a very fast filtration for the clarification of beetroot juice or cane sugar juice (for efficient saccharimetric tests of after lead acetate addition).

- ▶ filtraTECH's grade: FS90 (64 g/m²), smooth surface, for beetroot.
- ▶ Available in sheets (F) in pack of 500 sheets and pleated in 4 discs (C) in pack of 250 units.

| | 12 | P |
|----|-------|----|
| 40 | | CA |
| | | |
| 47 | THE P | |

| F | \checkmark |
|----------|--------------|
| Size | Code |
| 60x60 cm | FS90F6060D |



- ✓ filtraTECH's grade: FS91 (64 g/m²), creped surface, for clarification to sugar cane, fast filtration (// Whatman : 91),
- \checkmark Available in plain discs (A), folded discs (P) in box of 100 units, or in sheets (F) in pack of 500 units.

| A | ~ |
|------------|-----------|
| Ø Diameter | Code |
| 110 mm | FS91A0110 |
| 125 mm | FS91A0125 |
| 140 mm | FS91A0140 |
| 150 mm | FS91A0150 |
| 185 mm | FS91A0185 |
| 240 mm | FS91A0240 |

| P | ~ |
|------------|-----------|
| Ø Diameter | Code |
| 185 mm | FS91P0185 |
| 240 mm | FS91P0240 |



